

### CS60 2K HS Ready Mixed Colours - Satin

Date: 14-06-2017

Page: 1

#### DESCRIPTION

##### High density paint – solid colours

CS60 2K HS compliant ready mixed colours satin. Solid content (see formulation) % by weight (RFU).


The EU Value for this product (product category IIB .d) in ready for use form is max.420 grams of VOC Per litre. The VOC content of this product is less than 420 g/l.

Composition	Acrylic Resins,
Colour	See separate list
Shelf life	36 months in unopened container
Pack size	5 litre

Pre-treatment: 2-pack ready mixed colour must be applied on thoroughly sanded and degreased substrate.




Health and safety "For professional use only" **Important:** When using any **new** product, consult the "Health and Safety" data sheet. Always read the risks and precautions stated on the product label.



**Mix Ratio 3:1**  
2-pack colour  
FL2015 hardener



**Spraying viscosity**  
25 - 29 seconds BS4 flow cup – 17 seconds Din 4 flow cup at 20°C  
Pot life- 3 hours at 20°C



LVLP Compliant Gravity-feed spray gun  
HVLP gravity-feed spray gun  
Conventional gravity 1.4 – 1.6 3 - 3.5 bar



Number of coats 2 coats – 1 medium + 1 wet coat  
5 to 10 minutes flash off  
Film thickness 50 – 60 micron



Drying time at 20°C touch dry 4 – 6 hours through cure overnight polish within 24hrs  
Drying time at 60°C 20 - 25 min allow to cool polish then polish

The technical data contained herein is based on our present knowledge and we experience and we cannot be held liable for any errors, inaccuracies, omissions or editorial failings that result from technological changes or research between the date of issue of this document and the date the product is acquired. Before using the product, the user should carry out any necessary tests in order to ensure that the product is suitable for the intended application. Moreover, all users should contact the seller or the manufacturer of the product for additional technical information concerning its use if they think that the information in their possession needs to be clarified in any way, whether for normal use or a specific application of our product. Our guarantee applies within the context of the statutory regulations and provisions in force, current professional standards and in accordance with the stipulations set out in our general sales conditions. The information detailed in the present technical data sheet is given by way of indication and is not exhaustive. The same applies to any information provided verbally by telephone to any prospective or existing customer.